

Test Report MER25-00259.001

ALPHA GLOBAL SUPPLIES L.L.C.

The results shown in this test report specifically refer to the sample(s) tested as received unless otherwise stated. All tests have been performed using the latest revision of the methods indicated, unless specifically marked otherwise on the report. Precision parameters apply in the determination of the above (or below) results. Users of analytical results, when establishing conformance with commercial or regulatory requirements should note the full provisions of ASTM D3244, IP 367 and ISO 4259 in that context, the default confidence level of petroleum testing having been set at the 95% confidence level. Your attention is specifically drawn to Sections 7.3.6, 7.3.7 and 7.3.8 of ASTM D3244. With respect to the UOP methods listed in the report below (or above) the user is referred to the method and the statement within it specifying that the precision statements were determined using UOP Method 999. This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. This report shall not be reproduced except in full, without the written approval of the laboratory. Testing reports are not valid without signatory. Experimental result may be appealed at publishing the moment within 3 months.

Client Order Number:	--	SGS Order Number:	20092606
Client ID:	ALPHA GLOBAL SUPPLIES L.L.C		
Location:	Yeni İpek Yolu Antrepo	Product Description:	Bitumen
Sample Source:	--	Source ID:	--
Sample Type:	--	Sampled By:	SGS
Sampled:	21-Jan-2025	Received:	21-Jan-2025 14:00
Analysed:	10-Feb-2025 10:18	Completed:	10-Feb-2025 10:18
Seal No:	495013		
Sub-sample:	[1: 3 Litre Can];		
Report Comment:			

Property	Method	Result Unit	Min	Max
Penetration of Bituminous Materials	ASTM D5			
Penetration (25°C, 100g, 5s)		63 0.1 mm	--	--
Softening Point	ASTM D36	50.6 °C	--	--
Ductility	ASTM D113	>100 cm	--	--
Cleveland Flash Point (Open cup)	ASTM D92	286 °C	--	--
SG (Relative Density) at 25/25°C	ASTM D70	1.0591 --	--	--
Soluble Matter	ASTM D2042	99.89 % (m/m)	--	--
Spot Test of Asphaltic Materials	AASHTO T 102			
Spot Test		Negative --	--	--
Loss on Heating	ASTM D6	-0.04 % (m/m)	--	--
Retained Penetration	ASTM D1754/D1754M	79.37 %	--	--
Ductility at 25 °C after TFOT by ASTM D113	ASTM D1754/D1754M	>100 cm	--	--

End of Analytical Results

REPORTED BY

AUTHORISED SIGNATORY

Buket Mete
External Affairs and Reporting
Specialist

Kaan Gulburnu
Laboratory Manager

